



Burgdorf, 17.06.2020

**Test order No. 2020-0809**

Date of order: 03.06.2020  
Responsible:  
Pages: 2

---

**Methoden:**

JIS L 1902 Quantitative analysis for determination of the bacteriostatic activity:  
JIS L 1902 Determination of the anti dust mite effect:

---

**SANITIZED AG**

A handwritten signature in black ink, appearing to read 'E. Rohrbach', written over a horizontal line.

**Erich Rohrbach**  
Head Microbiology

The findings are valid for the tested object(s) only. Filing record of report and documentation is 10 years.

# SANITIZED AG

## Results

### Description of sample

Sample number: 2020-0809-01 Received: 03.06.2020  
Business: TEXTILE Type: QC

Identification: Microfibra 83  
Main Component: 100% PES  
Appearance: White (83g/m2)  
Field of Application: Pillows

Sanitized Products: Sanitized® T 99-19  
Declared quantity: 20g/l  
Finishing Process(es): Padding (pickup: 70%)

Finishing Parameter(s): Drying: 120°C  
Curing: 170°C - 30sec

Additive Finish: 60g/l Fluorocarbon

Remark: Production sample

### Test results of the SANITIZED-laboratory

Quantitative analysis for determination of the bacteriostatic activity:				
Method	Test point	Activity	Reduction in %	Evaluation
JIS L 1902	Staphylococcus aureus ATCC 6538	>5.30	>99.99	Good effect

  

Determination of the anti dust mite effect:				
Method	Test point	Evaluation		
JIS L 1902	Indication of the anti dust mite test	recommended		